



Nexus SG2

Copper coated solid mild steel wire for Semi-automatic and Robotic MIG/MAG welding applications

Mild steel MIG/MAG wires for welding mild and medium tensile Structural steels and plates using CO₂ and Mixed gases.

International Standards

BS EN 440:1995	AWS A5.18- 2001
G3Si1	ER 70S - 6

Typical All-Weld Metal Analysis (wt%)

C	Si	Mn	S	P
0.09	0.60	1.17	0.014	0.012

Typical All-Weld Metal Mechanical Properties

Yield Strength N/mm²	Tensile Strength N/mm²	Elongation %	Impact Strength -20°C (J)
452	545	24	115

Welding Positions

All Positions including vertical down
--

Materials

All mild and medium carbon steels with a toughness requirements down to -20°C
--

Packaging

Size mm	0.6	0.8	1.0	1.2	1.6
Plastic spools 5 kg	✓	✓	-	-	-
Plastic spools 15 kg	-	✓	✓	✓	✓
Wire basket 15 kg	-	✓	✓	✓	✓
250 kg Round Bulk Packs	-	✓	✓	✓	✓

Additional Information

CE Certified	Constructional products directive (CPD)
Certification	BS EN 10204:2004 Type 2.2
Material safety data sheet	MSDS 01
BOC Shielding Gas MIG	Argoshield Light (<3 mm)/Universal (3-10 mm)/Heavy (>10 mm)
Related Nexus Products	Nexus E6013/E7024 and Nexus A15/A18